



INFLUENCE OF NITROGEN-, PHOSPHORUS-, METAL-CONTAINING OLIGOMERS ON THE PHYSICAL AND MECHANICAL PROPERTIES OF COMPOSITE MATERIALS BASED ON POLYETHYLENE

Tojiyev Panji Jovliyevich¹

¹Termez State University Doctor of Technical Sciences, Associate Professor

E-mail: panjitojiyev74@gmail.com

Turaev Hayit Khudoynazarovich²

²Termez State University Doctor of Chemistry, Professor, Dean of the Faculty of Chemistry, TerSU

Nuraliev Gayrat Turaevich³

³doctoral student Termez State University

Jalilov Abdulakhat Turovovich⁴

⁴Doctor of chemical sciences, prof., academician of the Academy of Sciences of the Republic of Uzbekistan Tashkent Chemical Technology Research Institute, Republic of Uzbekistan, Tashkent
<https://doi.org/10.5281/zenodo.7246737>

Abstract.

The article studied the physical and mechanical properties of filled polyethylene and polyamide compositions, the determination of the melt flow index by vizkizometry methods, the determination of bending strength by the methods of two-bearing bending, the determination of Charpy impact strength.

The rheological characteristics of composite materials based on polyethylene with nitrogen-, phosphorus-, and metal-containing oligomers have been determined.

To obtain a composite material based on polyethylene, the content of nitrogen-, phosphorus-, metal-containing oligomers was changed from 1 mass to 5 mass parts. The data obtained show that the optimal compositions are those containing: 3 wt.h. nitrogen-, phosphorus-, metal-containing oligomers.

Key words: polyethylene, nitrogen-, phosphorus-, metal-containing oligomers, atomic force microscopy, physicochemical and mechanical properties.

Introduction. Today, the rapid growth of the world population and production volumes leads to a growing demand for polymer composite materials from year to year. In particular, the demand for polymer composite materials in industry and production is growing every day. In this regard, the automotive industry places high demands on the design of polymer materials.

Currently, the basis of scientific research is the production of composite materials that meet a number of requirements, such as modification of polymers, improvement of their physical and mechanical properties, addition of additives without changing their composition [1;2].

In the work, nitrogen-, phosphorus-, metal-containing oligomers were used as fillers in polymeric materials of various compositions (polyethylene), which showed the promise of using some compounds of this class as flame retardants [3].

Method and materials. The object of research is thermoplastic composite materials based on polyethylene and polyamide. Evaluation of the melt flow index (MFR), which is the selected temperature and viscosity of the medium molecular weight melt, is usually a quantitative benchmark for pipe manufacturers. The fluidity of a polyethylene melt and composites based on

it was determined in a capillary displacement viscometer under the action of a constant force type IIRT-M according to GOST 11645-73 (ASTM D 1238) [2] Determination of strength composites for bending was carried out according to GOST 4648-71 (ASTM D 638) [3] by the method of bilateral bending. The specimens were tested as 55.5 x 6 x 4 mm beams with a side spacing of 40 mm. The flexural strength was calculated using the following formula. $\sigma = 1.5 (Ra) / (bc^2)$

In this study, impact resistance was determined in accordance with GOST 4647-80 (ASTM D 638) according to Charpy [4]. The Charpy impact strength was calculated using the following equation: $\sigma = An / (ab)$ where σ is the Sharpe impact force; An - three times the dissipated impact energy of destruction of the sample without cutting; a , b - width and thickness of the middle part of the sample;

Sharpe exposure values were taken as the average of dozens of experiments performed on each sample. To test frost resistance, the samples were kept at minus 30 °C for 100 days and then their impact resistance was measured using the Sharpe method. The tensile strength and relative elongation of the sample were determined in accordance with GOST 11262-80 (ASTM D 638) [5]. These parameters were determined on a cutting machine with a strain rate of 50 mm/min on blade-shaped samples 50 x 6 x 4 mm in size. Tensile strength (σ) samples were determined according to the following equation: $\sigma = P / (a \cdot b)$, where P is the load; a , b - thickness and width of the narrowest part of the sample, mm. The elongation at break (ϵ) was determined by the equation $(\epsilon) = (\Delta L / L_0) 100\%$, taking into account the initial length of the sample (L_0) and the increase in its length at break (ΔL).

The discussion of the results. In this study, an improvement in the physico-mechanical properties of P-Y-342 polyethylene was observed. The aim of the work is to improve the physico-mechanical properties of polymers as a result of their addition of nitrogen-, phosphorus-, and metal-containing oligomers [6]. it's the same involves the development of methods for obtaining composite materials based on nanoscale modifiers that enhance the physical and mechanical properties of polymers and affect polymer macromolecules.

Experimental part. The process of chemical modification of polymers includes the improvement of their physical, mechanical and chemical properties by introducing new functional groups into the polymer macromolecule by copolymerization or crosslinking. [7] In this study, nanocomposites were obtained by modifying polyethylene with nitrogen-, phosphorus-, and metal-containing oligomers. Table 1 shows that the properties of nanocomposites based on polyethylene P-Y 342 filled with nitrogen-, phosphorus-, metal-containing oligomers have changed compared to the original polymers. The results of the analysis show that the inclusion of nanoparticles in the polymer improves the physical and mechanical properties of the polymers. [8]

Table 1.

Comparative analysis of the physical and mechanical properties of composite materials based on polyethylene P-Y 342 filled with nitrogen-, phosphorus-, metal-containing oligomers.

The composition of the composition	Impact strength, kJ/m ²	σ bending, MPa	fracture σ , MPa	Elongation, %	Shrinkage, %



	GOST 4647-80	GOST 4648-80	GOST 14236-81	GOST 14236-81	GOST 18599-21
P-Y 342	50	24	21	750	3
P-Y 342/3% CuO - NH ₄ PO ₃	56	35	33	174	2,7
P-Y 342/3% CoO - NH ₄ PO ₃	60	36	36	170	2,8
P-Y 342/3% NiO - NH ₄ PO ₃	68	38	48	155	2,2

By adding 3% NiO - NH₄PO₃ to polyethylene, it can be observed that the impact resistance increased from 50 to 68 kJ/m² compared to the original polyethylene, the bending resistance increased from 24 to 38 MPa, and the tensile strength increased from 21 to 48 MPa. [9-10]. Thus, the addition of 3% NiO - NH₄PO₃ to polyolefins led to high physical and mechanical properties of polymer composite materials. In all cases, it can be noted that the high hardness and strength of the results obtained were due to nitrogen-, phosphorus-, and metal-containing oligomers [11].

AFM (atomic force microscopy) is widely used to study the specifics of the microstructure and topography of various materials. This method is very sensitive to pixels and can form the surface of a sample taken in the nanoscale range on a three-dimensional surface. This method clearly shows the change in the surface, shape and size of the particles, as well as the mechanical properties of the surface of the material. [12]. Also, in this work, we studied the effect of particle modification with nitrogen-, phosphorus-, metal-containing oligomers on the surface morphology of the polymer. Analysis and study of the surface of modified polyolefins show that particles of nitrogen-, phosphorus-, and metal-containing oligomers are scattered among polymer macromolecules and interact. The analysis was carried out on an AFM using silicon cantilevers with a turning radius of 10 nm [13].




Figure 1. AFM images of a composite material based on polyethylene with nitrogen-, phosphorus-, metal-containing oligomers a) - three-dimensional image, b) - two-dimensional image.

The scanning area ranged from 1 to 50 μm. Microscopy was carried out in air by the semi-contact method; on the lines of registration of the change in the amplitude of oscillations of the counteraction axis, oscillations of the intermediate movement and the surface relief are reflected, which indicates the adhesion of individual surfaces to each other. On fig. 1 shows the surface of polyethylene modified with divalent nickel phosphates. The results show that the



roughness of pure polyethylene is 100 nm, and the surface roughness of alumina-modified polyethylene is 210 nm [14].

In this work, on the basis of thermoanalytical studies, the thermal-oxidative properties of the obtained composite materials are studied. It is known that polymer composite materials filled with nanocomposites particles with nitrogen-, phosphorus-, metal-containing oligomers decompose at higher temperatures than pure polymers, and this decomposition is characterized by the formation of an ash residue. This indicates the thermal stability of the obtained composite materials. Complex physical and mechanical properties of composite materials are determined on the basis of chemical changes composition of polymers during their processing. These processes take place at high temperatures. In this work, thermal and thermophysical properties were studied: a change in the melting point, heat resistance.

The melting temperature and crystallization rate of polymer composite materials were determined by differential scanning calorimetry (DSC). The results obtained are presented in table 2.

Table 2.

Thermodynamic properties of composite materials based on polyethylene P-Y 342 with nitrogen-, phosphorus-, metal-containing oligomers.

The composition of the composition	Startmelting, then C	Melting peak, T°C	Enthalpy, ΔN, J/g	Degree of crystallinity α, %
P-Y 342	220	224	188	55
P-Y 342/ 3% CuO - NH ₄ PO ₃	236	241	197	61
P-Y 342/ 3% CoO - NH ₄ PO ₃	237	243	203	59
P-Y 342/ 3% NiO - NH ₄ PO ₃	239	245	210	58

To determine the operating temperature range of polymers by differential scanning calorimetry (DSC), thermograms of samples filled with fillers were obtained.

Table 3.

Thermodynamic properties of composite materials based on polyethylene P-Y 342 with nitrogen-, phosphorus-, metal-containing oligomers

Состав композиции	Начало плавления, T°С	Пик плавления, T°С	Энтальпия, ΔН, Дж/г	Степень кристалличности α, %
P-Y 342	125	134	182	62
P-Y 342/3% CuO - NH ₄ PO ₃	136	147	199	68
P-Y 342/3% CoO - NH ₄ PO ₃	137	149	193	66
P-Y 342/3%NiO - NH ₄ PO ₃	139	153	190	65

A comparative analysis of the diffraction spectra of composite materials by types of fillers and polymers showed that the greater the interlayer distance of the modified fillers and the higher the filler concentration, the higher the diffusion rate of the filler included in the composition. Thus, the degree of dispersion of divalent metal phosphates in the polymer

composition also depends on the duration of mixing of the components and the viscosity of the melt.

Accurate results can be obtained in an experimental study of the size and shape of particles using X-ray phase analysis methods (Debye-Scherrer method). The size of coherent distribution zones (CZR) (the size of nanocrystals) is determined by the Debye-Scherrer formula: $D_p = K \lambda / (B \cos \theta)$

D_p - Average crystal size (nm) K - Scherrer's constant. K varies from 0.68 to 2.08. For spherical crystals with cubic symmetry $K = 0.94$

λ is the wavelength of X-rays. $Cu\ Ka = 1.54178 \text{ \AA}$.

B is the integral length of reflections in the FWHM diffractometer (full width at half maximum). $\cos\theta$ is the cosine angle of X-ray diffraction.

Table 4.

Results of calculating the size of nanoparticles of a composite based on P-Y 342 with nitrogen-, phosphorus-, metal-containing oligomers according to the Debye-Scherrer formula

Nº	2theta - Scan Angle	FWHM-integral reflection width	Dp (nm) average crystallite size	Dp(nm) average
1	8.2	0.478	17.42	15.61
2	8.7	0.57	14.61	
3	21.3030	0.5584	15.12	
4	24.0203	0.54	15.70	
5	26.2200	0.56	15.23	

According to the results of X-ray phase analysis, it was found that the particle size in the resulting composite materials is on the nanoscale.

Conclusions Thus, the maximum amount of nitrogen-, phosphorus-, metal-containing oligomers added as a filler to improve the physical and mechanical properties of polymer composite materials based on polyethylene was 3%. All the obtained results showed that the addition of 3% nitrogen-, phosphorus-, metal-containing oligomers to polymers increases the strength and thermal stability of polymers.

References:

1. UmarovSh.Sh., Tojiyev P.J., TuraevKh.Kh., Jalilov A.T. Structure and properties of polymers filled with metal oxides // Tashkent : Uzbek chemical journal, 2021, №4, bet -pp.18-24(in Russian)
2. DusanovR.Kh., TozhievP.Zh., TuraevKh.Kh., Jalilov A.T. Structure and properties of polyamide-6 filled with vermiculite Universum: chemistry and biology: electronic scientific journal. -2020.-№10(76). pp. 54-57(in Russian)
3. GOST 11645-73. Plastics. Method for determining the melt flow rate of thermoplastics. Enter. from 01.01.1975. M .: p. 12(in Russian)
4. GOST 9550-81 (Plastics. Methods for determining the modulus of elasticity in tension, compression and bending) Vved. from 26.08.1981 p. 15(in Russian)
5. GOST 4647-80. Plastics. Method for determining the Charpy impact strength. Enter. from 01.06.1981, S.27(in Russian)



6. GOST 11262-80. Plastics. Tensile test method. Enter. from 01.12.1980, P.16(in Russian)
7. GOST 4651-2014. Plastics. Compression test method. Enter. from 01.03.2015. M. : Standartinform, 2014, S.20(in Russian)
8. Chukov N.A. Composite materials based on polypropylene and nanoscale fillers: dissertation for a candidate of technical sciences: - Nalchik, 2011. - 110 p. : ill. RSL OD, 61 11-5 / 1845(in Russian)
9. Henini M., Quantum Dot Nanostructures // Materials Today. - 2002. - V. 48. -P. 140-142.(in English)
10. Kiviranta L., Kumpulainen S. Quality Control and Characterization of Bentonite Materials // Posiva OY.- 2011. - P.102. (in English)
11. Egorova O.V. Directed regulation of the structure and properties of polyethylene filled with dispersed fillers / OV Egorova, Yu.A. Kadykova, S.E. Artemenko // Plastic mass. - 2012. - No. 4. - S. 57-59. (in Russian)
12. Tojiev P.J., Normurodov B.A., Turaev Kh.Kh., Nurkulov F.N. *, Jalilov A.T. * Study of the physical and mechanical properties of highly filled polyethylene compositions // UNIVERSUM: Chemical technology: electronic scientific journal 2018 No. 2 (47). (in Russian)
13. Mozzhukhin V.B. Influence of technological equipment and technology for obtaining highly filled compositions based on polyolefins on their physical and mechanical properties / VB Mozzhukhin et al. // Plastics. - 2013. - No. 1. - P. 54-56.
14. B.A. Normurodov, P.J. Tojiev, Kh.Kh. Turaev, A.T. Djalilov, F.N. Nurkulov Study of physical and mechanical properties of basalt-containing polyethylene compositions // Tashkent: Composite materials-2017.-№ 4.-C.10-12(in Russian)
15. B.A. Normurodov, P.J. Tojiev, Kh.Kh. Turaev, A.T. Djalilov Synthesis and IR-spectroscopic study of sulfur-containing oligomer// UNIVERSUM: Chemistry and Biology: electronic scientific journal 2018 No. 2 (44). (in Russian)
16. Kryzhanovsky, V.K. Production of products from polymer materials textbook / VK Kryzhanovsky and [others]. - SPb. : Profession, 2014. -- 592 p. (in Russian)
17. Bredikhin P.A., Kadykova Yu.A. Investigation of the properties of PCM filled with dispersed basalt // V International student electronic scientific conference "Student scientific forum" - 2013. (in Russian)
18. Kerber M.L., Bukanov A.M., Wolfson S.I., Gorbunova Yu., Kandyrin L.B., Sirota A.G., Sheryshev M.A. Physical and chemical processes in the processing of polymers. - SPb.: Nauchnyeosnovyitekhnologii, 2013.
19. Guseva M.A., Structure and physical-mechanical properties of nanocomposites on the basis of non-polar polymers and layered silicates: Autoref. Dis. Cand. phys.-math. science Moscow: INXS RAN, 2004.
20. Kompozitnyy material na osnove polyolefinov / Pod ed. D. Nwabunmy, T. Cue. Per. s engl.-SPb.: NOT, 2014.
21. Osama Abdulkarim Al Khelo Material na osnove polypropylene with adjustable properties. Dissertation. sugar tech. science Moscow: RXTU, 20014.
22. Shitov D.Yu., Kravchenko T.P., Osipchik V.S., Rakov E.G. Kompozitnyy material na osnove polypropylenea s korbonnyimi nanopolnityami // Plasticheskie massy, No. 2, 2013. S. 29-33.

